

PRODUCT DATASHEET



PAROC Marine Slab VLO 150

Stone wool slab (cut to lamellas)

Fire insulation for shipbuilding applications.

Maximum service temperature for PAROC Marine Slab VLO 150 is 660°C.

PAROC stone wool products are capable of withstanding high temperatures. The binder starts to evaporate when its temperature exceeds approximately 200°C. The insulating properties remain unchanged, but the compressive stress weakens. The softening temperature of stone wool products is over 1000°C.

Type-Examination (Module B) certificate No. EUFI29-20002519-MED

Designation Code Nominal Density

150 kg/m³

MW-EN 14303-T5

Package Type Plastic packs on pallet

DIMENSIONS		
WIDTH X LENGTH	THICKNESS	
600 x 1200 mm	20 - 120 mm	
According to EN 822	According to EN 823	
Other Dimensions: Other dimensions available on request.		



Properties

PROPERTY	VALUE	ACCORDING TO	
FIRE PROPERTIES			
Fire Classification (IMO)	Non-Combustible	IMO FTP 2010 Code Part 1	
THERMAL PROPERTIES			
Thermal Conductivity in 50 °C, λ_{50}	0,042 W/mK	EN 12667	
Thermal Conductivity in 100 °C, λ ₁₀₀	0,046 W/mK	EN 12667	
Thermal Conductivity in 200 °C, λ_{200}	0,060 W/mK	EN 12667	
Thermal Conductivity in 300 °C, λ ₃₀₀	0,081 W/mK	EN 12667	
Thermal Conductivity in 400 °C, λ_{400}	0,110 W/mK	EN 12667	
Thermal Conductivity in 500 °C, λ ₅₀₀	0,147 W/mK	EN 12667	
Thermal Conductivity in 600 °C, λ ₆₀₀	0,192 W/mK	EN 12667	
MOISTURE PROPERTIES			
Water Absorption Short Term WS, (Wp)	≤ 1 kg/m²	EN 1609	



Head Office: PAROC GROUP, P.O. Box 240 (Energiakuja 3), FI-00181 Helsinki Finland, Tel. +358 46 876 8000, www.paroc.com

The information in this brochure describes the conditions and technical properties of the disclosed products, valid at the time of publication of this document and until replaced by the next printed or digital version. The latest version of this brochure is always available on the Paroc website. Our information material presents applications for which the functions and technical properties of our products have been approved. However, the information does not mean a commercial guarantee. We do not assume liability of the use of third party components used in the application or the installation of our products. We cannot warrant the suitability of our products if used in an area or conditions which are not provided in our information material. As a result of constant further development of our products we reserve the right to make alterations to our information material at any time. PAROC is a registered trademark of Paroc Group. This data sheet is valid in following countries: international use (general information).